

Technical Data Sheet

HU600

ABS

PRODUCT DESCRIPTION:

ABSHU600 is high heat resistance ABS with high rigidity, toughness and good UV-stability .

FEATURES:

- Ultra high heat
- High impact

APPLICATION:

- Console
- Luggage door garnish

Properties	Standard	Condition	Unit	Typical Value
Physical				
Density	ISO 1183	23°C	g/cm ³	1.06
Mold Shrinkage	ISO 294	23°C, 48hr	%	0.4-0.7
Poisson's Ratio	ISO 527	1mm/min	—	0.39
Mechanical				
Tensile Strength at Yield	ISO 527	50mm/min	MPa	43
Elongation at Break	ISO 527	50mm/min	%	20
Flexural Strength	ISO 178	2mm/min	MPa	65
Flexural Modulus	ISO 178	2mm/min	MPa	2450
Notched Charpy Impact	ISO 179	4J, 23°C	kJ/m ²	13
Notched Charpy Impact	ISO 179	4J, -30°C	kJ/m ²	7
Rockwell Hardness	ISO 2039-2	23°C	R-scale	108
Thermal				
Heat Deflection Temperature	ISO 75	120°C/hr, 0.45MPa	°C	101
Heat Deflection Temperature	ISO 75	120°C/hr, 1.80MPa	°C	92
Vicat Softening Temperature	ISO 306	50°C/hr, 5kg	°C	107
Other Properties				
Flammability	ISO 3795	360*100*3 mm	mm/min	≤80

Processing Parameters		Value	Unit
Pre-treatment			
Drying Temperature		85 ~ 95	°C
Drying Time		3 ~ 4	hour
Maximum Moisture Content		≤0.05	%
General Guidelines			
Barrel Temperature	Rear	200 ~ 220	°C
	Middle	230 ~ 240	°C
	Front	240 ~ 250	°C
Nozzle		250 ~ 260	°C
Melt Temperature		240 ~ 260	°C
Mold Temperature		50 ~ 80	°C

Note :

1. Values are measured at 23°C and in RH of 50% on injection molded specimens.
2. Typical values for uncolored products, not specifications, and may vary slightly with different colors.
3. Flexural strength is tested with fixed deflection.
4. HDT: specimens are unannealed.
5. The general guidelines are only for reference. Exact settings have to follow the product and machine conditions.

Disclaimer :

To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the data compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or process described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. You may not copy this document to a web site.

Kumho-Sunny expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication.